

E-mail generale: info@deltaphoenix.it
Laboratorio: tech@deltaphoenix.it
Amministrazione: admin@deltaphoenix.it
www.deltaphoenix.it

STUCK B
Cement with chemical binder
TECHNICAL DATA SHEET

Main Component :	Bauxite	
Maximum use temperature:	[°C]	1600
Average grain size:	[mm]	0÷4
Chemical analysis:	[%]	Al ₂ O ₃ + TiO ₂ : 82÷84
	[%]	SiO ₂ : 11÷13
	[%]	P ₂ O ₅ : 2÷3
Water quantity:	[L/100 kg secco]	7÷9
Installation quantity:	[kg/m ³]	2650
Warnings:	Plastic gloves	
Application:	By trowel and/or by hand	
Drying and firing:	250°C	

NOTES:

Packing: Sac of 25 kg on pallet of 1000 kg.

Preservation: 12 months in its own packing far from heat sources. Storage temperature: 5÷35 °C

Main appliances:

➤ Repairing of silico-aluminous refractory

Considering the quality of the raw materials, there can be slight differences in the above data which do not commit our technical department. We reserve the right to change some of the above data without previous information and according to our unobjectionable judgement.