

E-mail generale: info@deltaphoenix.it
Laboratorio: tech@deltaphoenix.it
Amministrazione: admin@deltaphoenix.it
www.deltaphoenix.it

TIXOBOND 27
Ready to use paint
TECHNICAL DATA SHEET

Main Component :	Zircone	
Maximum use temperature:	[°C]	1700
Average grain size:	[mm]	0÷0.1
Chemical analysis:	[%]	Al ₂ O ₃ +TiO ₂ : 24-26
	[%]	SiO ₂ : 27 - 30
	[%]	ZrO ₂ : 45 - 48
Installation quantity:	[kg/m ³]	2400 - 2600
Application:	By brush previous to mix	
Drying and firing:	150°C	

NOTES:

Packing: Plastic barrels of 30 Kg.

Preservation: 12 months in its own packing far from heat sources. Storage temperature: 5÷35 °C. N.B. DO NOT FREEZE

Main appliances:

- Cement for quartz, zircon, aluminium bricks.
- Protective cement for aluminium furnaces

Considering the quality of the raw materials, there can be slight differences in the above data which do not commit our technical department. We reserve the right to change some of the above data without previous information and according to our unobjectionable judgement.