

E-mail generale: [info@deltaphoenix.it](mailto:info@deltaphoenix.it)  
Laboratorio: [tech@deltaphoenix.it](mailto:tech@deltaphoenix.it)  
Amministrazione: [admin@deltaphoenix.it](mailto:admin@deltaphoenix.it)  
[www.deltaphoenix.it](http://www.deltaphoenix.it)

**TIXOBOND AL**  
Ready to use paint  
**TECHNICAL DATA SHEET**

Main Component :	Zirconium	
Maximum use temperature:	[°C]	1200
Average grain size:	[mm]	0÷0.1
Chemical analysis:	[%]	Al <sub>2</sub> O <sub>3</sub> +TiO <sub>2</sub> : 3
	[%]	SiO <sub>2</sub> : 30
	[%]	MgO+CaO+K <sub>2</sub> O+Na <sub>2</sub> O:6
	[%]	ZrO <sub>2</sub> : 58
Installation quantity:	[kg/m <sup>3</sup> ]	2400 - 2600
Application:	By brush previous to mix	
Drying and firing:	150°C	

**NOTES:**

Packing: Plastic barrels of 25 Kg.

Preservation: 12 months in its own packing far from heat sources. Storage temperature: 5÷35 °C

Main appliances:

- Detaching material for aluminium

Considering the quality of the raw materials, there can be slight differences in the above data which do not commit our technical department. We reserve the right to change some of the above data without previous information and according to our unobjectionable judgement.