

E-mail generale: info@deltaphoenix.it
Laboratorio: tech@deltaphoenix.it
Amministrazione: admin@deltaphoenix.it
www.deltaphoenix.it

TIXOBOND W3
Ready-to-use cement
TECHNICAL DATA SHEET

Main Component :	Aluminium Silicate
Maximum use temperature:	[°C] 1150
Analisi chimica dopo cottura a 150°C:	[%] $\text{Al}_2\text{O}_3 + \text{TiO}_2$: 16-17
	[%] $\text{MgO} + \text{CaO} + \text{K}_2\text{O} + \text{Na}_2\text{O}$: 37-38
	[%] SiO_2 : 42-43
	[%] ZrO_2 : 5-6
Installation quantity:	[kg/m ³] 1400 - 1500
Application:	By brush previous to mix
Drying and firing:	90-150°C

NOTES:

Packing: Plastic Barrels of 20 kg or 6Kg

Preservation: 12 months in its own packing and far from heat sources. Storage temperature: 5-35 °C

N.B.: DO NOT FREEZE

Main appliances:

- Detaching and protective cement for aluminium
- Detaching and protective cement for cast iron containers for the aluminum transport

Considering the quality of the raw materials, there can be slight differences in the above data which do not commit our technical department. We reserve the right to change some of the above data without previous information and according to our unobjectionable judgement.